

1. PRODUCT NAME

Tenon® Cure & Seal

2. MANUFACTURER

TCC Materials®

2025 Centre Pointe Blvd.

Mendota Heights, MN 55120 USA

Phone: 1.651.688.9116

Fax: 1.651.688.9164

Internet: tccmaterials.com

3. PRODUCT DESCRIPTION

Tenon® Cure & Seal is a clear, non-yellowing, fast drying, acrylic compound. No fillers, oils, waxes or saponifiable resins are contained in the mixture. It is used for curing, sealing, and dustproofing freshly-placed and/or existing concrete, terrazzo, brick, stone, architectural concrete, and other cementitious materials. It forms a membrane film on new concrete to seal and retain hydration water, providing optimum curing of the substrate, and resistance to abrasion damage caused by salt, oil, grease, mild acids, and alkali. It also resists stains from soot, smog, fumes, and gases. Cure & Seal benefits existing concrete by penetrating into the slab, binding together the small dusting particles, while filling the voids to produce a hard, dust-free, brighter surface. When used on terrazzo, brick, stone, and architectural concrete, it brings out the highlights, as well as enriches and enhances the natural colors found in the material.

Features and Benefits

- Cures in 1-2 hours
- Increases optimum cure of new concrete
- Protects concrete surfaces from dirt and damage
- Enhances colors, darkens the appearance of surface
- Ready to use (no diluting)
- Goes on clear, dries clear
- Chemical resistant
- Meets Federal EPA's VOC requirements
- Easy to apply with sprayer or roller
- Makes job site clean-up easier, construction debris does not adhere
- Compatible with many resilient tile and carpet adhesives
- Can improve adhesion efficiency for longer life to the floor covering
- Often recommended for concrete surfaces that will be carpeted

Uses

- Cure, and seal surfaces
- Exterior applications or interior when properly ventilated
- Concrete or masonry applications
- New or existing applications
- Terrazzo, brick, stone, pavers, and other cementitious materials
- Commercial, and residential applications

SAFETY

READ THE SAFETY DATA SHEET (SDS) BEFORE USING THIS PRODUCT. SDS information is available on our website: tccmaterials.com or contact TCC Materials® at 651-688-9116 (7:30 AM to 4:00 PM Central US Time).

CAUTIONS

Read complete cautionary information printed on product container prior to use. This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered Tenon brand product (s) under normal environmental and working conditions. Because each project is different, neither Tenon nor TCC Materials® can be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

Typical Results of Tenon Cure & Seal	
Composition and Materials	A clear acrylic copolymer blended with fast drying aromatic hydrocarbon. No fillers are used, and there are no oils, waxes or saponifiable resins. Tenon products are manufactured with only the finest quality raw materials available and close quality-control is practiced.
Percent Solids	29%
Flash Point	>100°F (37°C)
Moisture Efficiency:	Meets ASTM C-1315 when applied to 300 sq. ft. per gal. (Max. allowed 0.40 kg/m²)
Typical Drying Time @ 70°F	1 hour (touch) 2 hours (traffic)
VOC Content	< 700 g/l
A.I.M. Category	Curing and Sealing Compound Maximum VOC: 700 g/L
Applicable Standards	ASTM C-1315, Type 1, Class A, B, & C ASTM C-309, Type 1, Class A, B and Type 1D with a red dye added. Fed. TT-C-800A, Type 1, Class 1 AASHTO Des. M-148, Type 1, Clear USDA Authorization for use in meat, poultry, and food processing plants. Resilient Tile Institute approval for compatibility with most resilient tile, carpet adhesives, and paints

Note: These dry times are dependent on normal drying conditions. Cool temperatures or high humidity will slow the drying time.

Packaging

- 1 gal. bottle (3.78 L) - Product #120839
- 5 gal. pail (18.93 L) - Product #120838
- 55 gal. drum (208 L)

Shelf Life

For best use, the recommended shelf life is 12 months. If shelf life is beyond 12 months, please contact your distributor. Store in the original labeled container, away from moisture, out of direct sunlight. DO NOT STORE NEAR HEAT OR OPEN FLAME. Keep containers tightly sealed when not in use.

5. INSTALLATION

Preparation

- Read all directions before starting work. Read and understand SDS pages for safety precautions prior to use.
- Remove all loose or unsound materials prior to application. Thoroughly clean surface of dirt, dust, oil, grease, or other contaminants before using.
- Apply only to dry surfaces for optimal performance. Do not apply when rain is expected within 4-6 hours of application.
- Use only in well-ventilated areas.

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

Job Mockups

The manufacturer requires that when its Tenon products are used in any application or as part of any system that includes other manufacturers' products, the contractor and/or design professional shall test all the system components collectively for compatibility, performance and long-term intended use in accordance with pertinent and accepted industry standards prior to any construction. Written documentation of the tests performed shall be satisfactory to the design professional and contractor. Test results must include the means and methods of application, products used, project-specific conditions being addressed, and standardized tests performed for each proposed system or variation.

Mixing

- Mixture may be gently stirred to blend prior to use. Do not entrain air.
- Do not dilute.

Application

Apply when both air and surface temperatures are above 40°F (4.4°C) and the Cure & Seal is above 50°F (10°C). For best results, apply uniformly at the specified rate of coverage. When using an airless sprayer, it should be equipped with PVC, viton, or other compatible fittings and hoses as solvents can damage rubber.

NOTE: Cure & Seal will darken the appearance of new concrete, especially if it is applied too heavily. A small mock-up in an inconspicuous area is often done to test compatibility with the substrate prior to full application.

New Concrete (Curing):

Finish troweling new concrete. Allow surface water to dissipate. Use a low-pressure or power sprayer to apply uniformly at the specified rate of coverage. Avoid heavy accumulation.

Existing Concrete (Sealing):

Remove all loose or unsound materials prior to application. Thoroughly clean surface of dirt, dust, oil, grease or other contaminants before using. Apply only to dry surfaces for optimal performance. Using a short-nap roller, or low-pressure sprayer to apply product evenly. Avoid heavy accumulation. A second coat may be applied on very porous surfaces with rapid absorption. Allow the product to become tack-free between coats.

Cleaning

Use mineral spirits or solvent-based cleaners, such as xylene on tools and equipment. For sprayers, pump the solvent through the spray equipment to remove residue and prevent clogs. For skin contact, wash thoroughly with soap and warm water.

Limitations

- Apply when both surface and air temperatures above 40°F (4.4°C).
- Not for use on asphalt or surfaces that are subject to immersion or constant liquid contact.
- Not for use where spillage of solvents, fuels, or brake, transmission, or hydraulic fluids, etc. are expected.
- Sprayers must be equipped with PVC, viton, or other compatible fittings and hoses as rubber or other materials will disintegrate from the solvent.
- Some fumes may be present during application. Use best practices when applying on interiors for proper ventilation.
- Concrete mixes containing calcium chloride will remain dark longer when sealed. Some extenders and additives, such as fly ash for example, can create inconsistent porosity and coverage ratios will need to be adjusted to compensate for these variations.
- Popout or scaling issues can occur with any concrete installation, but are more likely in extreme hot weather conditions (above 90°F / 32°C), and when finished by heavy steel troweling. In certain regional areas a reaction between the silica in the shale particles and the sodium and potassium alkali in the Portland cement can increase the occurrence. Where this type of shale is present, and extremely hot weather conditions prevail, it is recommended that liquid membrane curing compounds should not be used until the concrete has been completely cured by water ponding, continuous water spray mist, or wet burlap covering for a period of three days. A seal coat can then be applied for dustproofing and protection (when concrete is completely dry).
- When using a liquid release, you must check with the manufacturer to ensure proper washing has taken place before using Cure & Seal. If the liquid release has an abundance of oil, it will deter adhesion of the sealer. When using a powder release, care needs to be taken to ensure that the proper amount of release is washed off the surface or delaminating of the sealer may occur. This happens more often with lighter colors.

- Eliminate all sources of ignition. In case of fire use foam, CO₂, dry chemical. Do not use water spray. If spilled, contain spilled material and remove with inert absorbent. Dispose of the contaminated absorbent, container, and any unused contents in accordance with local, state, and federal regulations.
- Do not dilute with water or solvents.
- Allow sealer to warm to 50°F (10°C) before application.
- Keep containers tightly sealed when not in use.
- Keep out of reach of children.

Coverage

Approximate Coverage @ 70°F (21°C)	Sq. Ft./Gal.	M ² /L
Curing	300-500	7.3-12.3
Dustproof / Seal	300-500	7.3-12.3
Second Coat	400-800	9.8-19.6
Renovation Dustproof / Seal	300-400	7.3-9.8

Note: Coverage is per coating and may vary due to porosity, wind, temperatures, and condition of surfaces.

6. AVAILABILITY

To locate Tenon® products in your area, please contact:

Phone: 1.651.688.9116
Email: info@tccmaterials.com

7. WARRANTY

Seller warrants that its product will conform to and perform in accordance with the product specifications. The foregoing warranty is in lieu of all other warranties, expressed or implied, including, but not limited to those concerning merchantability and fitness for a particular purpose. Because of the difficulty in ascertaining and measuring damages hereunder, it is agreed that Seller's liability to the Buyer shall not exceed the total amount billed and billable to the Buyer for the product hereunder.

8. MAINTENANCE

Minimal maintenance is required other than normal sweeping, dusting, or mopping. If wear patterns do occur, or if spillage removes the coating, reapply to the affected area.

9. TECHNICAL SERVICES

Technical Assistance:

Information is available by calling TCC Materials®
(hours 7:30 AM to 4:00 PM CST):

Phone: 1.651.688.9116
Email: info@tccmaterials.com
Web: tccmaterials.com

Technical and Safety Literature:

To acquire technical and safety literature, please visit our website at: tccmaterials.com.

10. FILING SYSTEM

Division 9



2025 Centre Pointe Blvd.
Mendota Heights, MN 55120
©Copyright 2025 TCC Materials®

REV 07/25