

REPAIR & RESTORATION



	CONSTRUCTION GROUT	VERTICAL REPAIR CI	VINYL CONCRETE PATCH	CRITICAL PAVEMENT REPAIR (CPR)	COMMERCIAL DOT REPAIR	INSTANT ANCHORING CEMENT	INSTANT HYDRAULIC CEMENT
	Construction Grout Television opposition of including security of the construction of	TENON TO A MARKET Vertical Repair Formally, the form of a familiar to the f	Vinyl Concrete Patch But stands and an option and to the Concrete Patch To have only a concrete production for the Concrete Patch Calley graded and the Concrete Patch Why Concrete Pa	Critical Pavement Repair Total Control of the Cont	TENON Commercial DOT Repair Fragge and the second of the	TENON Instant Anchorin Cement STENON Within Endering Cement Within Endering Cement	Instant Hydraciic Central W TENON Instant Hydraciic Central W TENON W T
USES:	 General purpose structural grouting Column bases, anchor bolts, equipment bases Interior/exterior, above or below grade 	 Vertical & overhead Patch honeycombs, voids Can be shaved/molded 	General purpose patchHorizontalVertical	 High-traffic concrete pavement repairs Parking structures, bridges decks, precast concrete, industrial floor repairs Airport runways 	 Highway repair & overlay Bridge & parking decks Freezer rooms 	Interior/exterior Set fasteners & fixtures Concrete/masonry	Plug holesAbove or below gradeStops active leaks
ADVANTAGES:	 Non-shrink/non-metallic Pumpable/flowable ASTM C1107 Can be accelerated for cold with Tenon® Fast-Set Liquid Activator 	7,000 psi in 7 daysNon-sag, non-shrinkExcellent durability	High-strengthPolymer-modifiedExcellent durability	 Polymer-modified for excellent bond Fiber reinforced for high flexural strength 	 Early strength +3,500 psi Polymer-modified MNDOT approved 	Expands as it hardensEasy water mixFast-setting	Bonds to wet substratesEasy water mixInstant setting
				APPLICATION			
Application	Trowel, pour, pump	Trowel	Trowel	Trowel	Trowel, pour, pump	Pourable	Trowel or hand apply
Horizontal/Vertical	Horizontal	Vertical & overhead	Horizontal & vertical	Horizontal & vertical	Horizontal	Horizontal	Horizontal, Vertical, Overhead
Thickness/Layer	1/2" - 4"	3⁄4" - 2"	Featheredge - 2"	1/2" - 4"	½" - 2" (can be extended)	-	-
28-Day Strength	10,500 psi (72.4 MPa)	8,000 psi (55.2 MPa)	7,000 psi (48.2 MPa)	5,000 psi (34.5 MPa)	8,500 psi (58.6 MPa)	10,000 psi (68.9 MPa)	5,500 psi (37.9 MPa)
Pot Life	15-20 minutes	10-15 minutes	20-30 minutes	20-30 minutes	10-15 minutes	15-20 minutes	2-4 minutes
Initial Set Time	20 minutes	15 minutes	30 minutes	15-25 minutes	20 minutes	15 minutes	2-3 minutes
Final Set Time	30 min-3 hours	30 minutes	60 minutes	20-30 minutes	25 minutes	20 minutes	3-5 minutes

COMPLIMENTARY PRODUCTS



AIR ENTRAINMENT

- Improves workability & freeze/thaw resistance
- Reduces segregation & bleeding
- Improves plasticity, water retention & cohesiveness of mortar



SET ACCELERATOR

- Non-chloride accelerator
- Non-corrosive
- Accelerates initial/final set & curing times
- Improves workability



MIGHTY BOND

- Solvent free/VOC compliant
- Increases tensile strength
- Enhances adhesion & durability
- Improves workability & curing



CONCRETE & MASONRY DISSOLVER

- Does not contain any harmful acids
- 100% biodegradable
- Non-corrosive & nonfuming



REFRACTORY MORTAR

- Applications of up to 2550°F
- Once cured becomes water insoluble & acid resistant
- For setting brick and flues



SALT BARRIER

- Non-film forming, will not create a slippery surface
- Protects against salts and chlorides
- Vapor permeable does not trap moisture



SALT BARRIER WB

- All attributes of Tenon Salt Barrier
- Low VOC Meets AIM VOC Regulations
- Low odor, allows for interior applications



BURNISHED BLOCK SEALER

- High-performance methacrylate polymers
- Non-yellowing
- Protects surface with high gloss finish



BURNISHED BLOCK SEALER WB

- Low VOC Meets AIM VOC Regulations
- Enhances color & adds
- a satin sheen
 Surface reacting, non-
- yellowing

 Breathable coating



RESTORATION CLEANER

- Cleans & restores concrete, masonry, & stone
- Removes efflorescence, light rust, & organic stains
- Mildly aggressive, will not deeply etch surface